



Standard Product Availability – Reflective Aluminum

Anolux [®] Anodized Grades	Photometric Properties				Mechanical Properties			
	Minimum % Total Reflectivity	Image Clarity DI	% Diffuse Reflection	Specular Reflectivity (Min.)	Temper	Tensile (Ksi)	Yield (Ksi)	Standard Sheet Size
Anolux [®] I Specular Mirror Finish	86	93	< 20	72 %	H-28	14.5-20.3	10.2-16.0	.020 X 48.5" X 96" & .020 X 49.212" X 96"
Anolux [®] III Specular Mirror Finish	87	94	< 14	83 %	H-19	23.2-29.0	20.3-26.1	.025 X 49.212" X 96"
Anolux [®] 412GS Specular Mirror Finish	87	95	< 6	84 %	H-19	23.2-29.0	20.3-26.1	.020 X 39.370" X 96"
Anolux [®] 610G Semi Specular Finish	84	28 - 56	65 - 72	•	H-34	21.8-26.9	20.3-25.4	.020 X 48.500" X 96"
Hammertone Embossed Finish	86	•	86	•	H-28	23.2-29.0	21.8-27.6	.020 X 49.212" X 96" & .025 X 49.212" X 96"
Pebbletone Embossed Finish	86	•	86	•	H-28	23.2-29.0	21.8-27.6	.020 X 39.370" X 96"
Anolux Golden Grow [®] Embossed Gold Finish	72	•	50-60	•	H-28	24	23	.020 X 49.212" X 96"
Anolux MIRO[®] PVD Enhanced[™] Grades								
Anolux MIRO-SILVER Enhanced [™] Specular Mirror Finish	98	97	< 6	94%	H-19	23.2-29.0	20.3-26.1	.020 X 48.5" X 96"
Anolux Miro [®] IV Enhanced [™] Specular Mirror Finish	95	95	< 12	90 %	H-19	23.2-29.0	20.3-26.1	.020 X 48.5" X 96" & .025 X 48.5" X 96"
Anolux Stucco Miro [®] 9 Enhanced [™] Embossed Specular Mirror Finish	95	n.m.	94	•	H-28	23.2-29.0	21.8-27.6	.012 X 49.212" X 96"
Anolux Miro [®] 5011 Enhanced [™] Diffuse Matt Finish	94	n.m.	80-90	•	H-19	23.2-26.9	21.8-25.4	.020 X 49.212" X 96"
Painted White Grades								
Whitelite [®] 90 Painted Aluminium	90	•	•	•	H-14	23.0	20.0	.020 X 48.5" X 96"

Custom Blank Sizes available upon request - minimum order requirements may apply

Slit Coil available upon request – minimum order requirements may apply

25-Year Warranty*: Anolux Miro[®] & Anolux [®] Grades

10-year Warranty*: Whitelite[®] 90

Anomet Inc. is registered to the ISO 9001:2000 standard of quality